



# MACH 1

## UHMPE Polymer Sheet

### Physical Properties

Ultra high Mechanical Polyethylene (UHMPE) is a superior resin engineered to operate in demanding applications combining low co-efficient of friction, excellent abrasion resistance and high impact. Mach1 UHMPE sets the standard for general purpose engineered plastic applications by combining wear, low friction, corrosion resistance and impact strength. Mach1 UHMPE retains key physical properties in sub-zero temperatures and is resistant to chemical attack. This resin is UV protected for outdoor applications. FDA contact and non-contact uses are acceptable as this resin complies with FDA regulations.

### TECHNICAL INFORMATION

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	g/cm <sup>3</sup>	0.929
Tensile strength	ASTM D-638	psi	5,600
Tensile modulus	ASTM D-638	psi	82,000
Elongation at break	ASTM D-638	%	450
Flexural modulus	ASTM D-790	psi	125,000
Flexural strength	ASTM D-790	psi	4,400
Izod impact, notched	ASTM D-4020	ft-lbs/in <sup>2</sup>	no break
Compressive modulus	ASTM D-695	psi	80,000
Compressive strength (10% Def.)	ASTM D-695	psi	2,900
Hardness	ASTM D-2240	Shore D	66
Coefficient of Friction - Dynamic	1018 Steel = 100	-	0.11
Coefficient of linear thermal expansion	ASTM D-696	in/in/°F	4.8 x 10 <sup>-5</sup>
Heat deflection temperature, 66 psi	ASTM D-648	°F	169
Environmental Stress Crack Resistance	ASTM D-1693	100% Igepal	> 750 hrs
Volume resistivity	ASTM D-257	Ohm-cm	>10 <sup>13</sup>
Surface resistivity	ASTM D-257	Ohm	>10 <sup>13</sup>
Brittleness Temperature	ASTM D746	°F	< - 103
Vicat softening temperature	ASTM D-1525	°F	248
Max. operating / service temp (air)		°F	175
Water absorption 24hrs.	ASTM D-570	%	0.01

\*All values are determined on specimens prepared according to ASTM 1248-84 "Standard Specifications for Polyethylene Plastic Molding and Extrusion Materials". Nominal values should NOT be interpreted as specifications.

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representations or warranty that such use is free of patent infringement and are not recommendations to infringe any patent.