

Densilite is a polymer sheet designed to replace traditional solid plastic and wood sheets. Densilite is formed from high molecular weight polyolefin resin utilizing a patented extrusion molding process. This makes an exceptionally strong and rigid sheet! Densilite is a unique homogeneous controlled density polymer sheet made to exacting standards. It possesses excellent dielectric and insulating properties due to its structure as a non-polar hydrocarbon polymer. With a water absorption rate very close to 0%, this sheet can withstand high-pressure washing and has excellent chemical resistance. The surface of each sheet is engineered for easy cleaning. Densilite is an ideal panel for the many applications including; chemical handling equipment, wall liners, corrosive atmospheres, high humidity or permanently damp locations, and fabrications which include cabinetry.

TECHNICAL INFORMATION

Property	Method	Unit	Nominal Value*
Density	ASTM D-792	g/cm ³	0.721
Tensile strength at yield	ASTM D-638	psi	3200
Tensile modulus	ASTM D-638	psi	180,000
Elongation at yield	ASTM D-638	%	n/a
Elongation at break	ASTM D-638	%	n/a
Tensile impact	DIN 53448	ft-lbs/in ²	n/a
Flexural modulus	ASTM D-790	psi	165,000
Flexural strength	ASTM D-790	psi	4900
Izod impact	ASTM D-4020	ft-lbs/in ²	no break
IZOD impact notched	ASTM D-2240	ft-lbs/in ²	no break
Compressive modulus	ASTM D-695	psi	n/a
Compressive deformation	ASTM D-621	% at 1000 psi	n/a
Hardness	ASTM D-2240	Shore D	78
Screw holding strength	ASTM D-1761	Unitless	620
Coefficient of linear thermal expansion	ASTM D-696	in/in/°F	5.0 x 10 ⁻⁵
Heat deflection temperature, 66 psi	ASTM D-648	°F	169
Heat deflection temperature, 264 psi	ASTM D-648	°F	n/a
Volume resistivity	ASTM D-257	Ohm-cm	>10 ¹⁵
Surface resistivity	ASTM D-257	Ohm	>10 ¹⁵
Vicat softening temperature	ASTM D-1525	°F	n/a
Max. operating temp.		°F	155
Water absorption 24hrs.	ASTM D-570	%	0.1

*All values are determined on specimens prepared according to ASTM 1248-84 "Standard Specifications for Polyethylene Plastic Molding and Extrusion Materials". Nominal values should not be interpreted as specifications.

NOTICE: All statements, information, and data given herein are believed to be accurate and reliable but are presented without guaranty, warranty, or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representations or warranty that such use is free of patent infringement and are not recommendations to infringe any patent.